



Dynamic Microchamber

Accuracy, Speed, Ease-of-Use

The Dynamic Microchamber (DMC) is the standard for small scale formaldehyde emissions tests for composite panel manufacturers in the United States and Canada. Used by the majority of members of the Composite Panel Association, the DMC has been sold to manufacturers on 4 continents since its development.

Approved by the United States Environmental Protection Agency, the DMC has 0.9769 R-squared correlation to the Large-Scale Chamber test.

Panel producers like the DMC because it's fast. After conditioning, samples can be tested and produce reliable results within just 15 minutes and it can perform

13 tests in less than 4 hours. The DMC can provide the fastest results compared to other EPA-approved test methods.

Not only is it fast, the DMC is easy to use. With full computer integration, the DMC software can produce test results with just a few clicks of a mouse. This means reports can be generated efficiently and technicians can be trained quickly, providing capable support for quality managers.

In addition to the standard emissions test, the DMC performs an equilibrium test, a mass transfer test, and the ASTM 6007-14 Small Chamber Test. These tests can provide a wealth of information to technical personnel trying to optimize the manufacturing process to reduce emissions, resin costs, or press times.

Technical Support, Parts and Service

To quickly and easily purchase hardware, consumables and parts; to schedule technical service and training; or to obtain a quote for a new DMC, visit bakelite.com.

Product Specifications

Testing Capabilities

- ASTM D-6007 (14) - Standard Test Method ... Using a Small-Scale Chamber
- Cs Steady State Emissions Test - Gas Analyzer
- Ceq Equilibrium Emissions Test - Gas Analyzer

Testing Materials

- Particleboard
- Medium Density Fiberboard (MDF), thin MDF
- Door Core
- Hardwood Plywood (Veneer Core or Composite Core)

Sample Size (expected)

3 x 15" x 7.875" (3 x 381 mm x 200 mm)

Chamber

Internal Dimensions (W x H x L)	7.97" x 13.75" x 24.53" (20.24 cm x 34.93 cm x 62.31 cm)		
Testing Volume	2750 m ³ (0.045 m ³)		
Material of Construction	Stainless Steel (304)		
Ventilation	0-20 sL/min		
Permissible Temperature	77° F ± 5 (25° C ± 2.8)		
Permissible Relative Humidity	50% ± 4		
Air Circulation	49 ft ³ /min (83 m ³ /h)		
Air Changes	> 3 ACH per test		
External Dimensions	Length: 34.6" (87.9 cm)	Width: 16.8" (42.7 cm)	Height: 16.4" (41.7 cm)

Testing Parameters – Gas Analyzer

Sensor Type	Electrochemical					
Sample Time	15 min/sample					
Calibration Time	30 minutes to 2 hours					
Accuracy	0.005 ppm					
Resolution	0.0001 ppm					
Method of control/reporting	Computer-integrated					
Interferences (amount of gas required to reflect 0.01 ppm change)						
	Gas	PMM	Gas	PMM	Gas	PPM
	H2	>100	Isopropanol	10	HCL	0.35
	Acetone	>10	CH3OH	6.3	NO2*	0.35
	Methyl ethyl ketone	>10	NO	5	Acetaldehyde	0.17
	Phenol	>10	NH3	3	Cl2*	0.07
	CO	56	Glutaraldehyde	2	H2S	0.03
	n-butanol	32	Propionaldehyde	1.6	SO2	0.3
	n-propanol	20	Ethanol	1.3	*Negative interference	

Requirements

Power	120 VAC, 50-60 Hz (2000 VA UPS Recommended)
Operating System	Windows XP® or newer
Background formaldehyde	<0.02 ppm





Next Generation Synthetics

Infinite potential.
Infinite curiosity.
Infinite solutions.

Atlanta, GA
Headquarters



Learn more about the vision, products
and history of bakelite on our website

bakelite.com

The information provided herein was believed by BAKELITE UK Holding Ltd. and its affiliated companies ("BAKELITE SYNTHETICS") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by BAKELITE SYNTHETICS are subject to BAKELITE SYNTHETICS' terms and conditions of sale. BAKELITE SYNTHETICS MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY BAKELITE SYNTHETICS.

© 2022 BAKELITE. All rights reserved.

® and ™ denote trademarks owned or licensed by BAKELITE SYNTHETICS.